COMMENT

Cite this: Phys. Chem. Chem. Phys., 2014, 16, 4394

Comment on "Volume shrinkage of a metal-organic framework host induced by the dispersive attraction of guest gas molecules"

François-Xavier Coudert,*^a Alain H. Fuchs^a and Alexander V. Neimark^b

Received 24th September 2013, Accepted 2nd January 2014

DOI: 10.1039/c3cp54042a

www.rsc.org/pccp

In a recent paper,¹ Joo *et al.* report from density functional theory calculations that H₂ adsorption on MOF-5 leads to a contraction of the metal-organic framework's unit cell. The authors contrast that finding with "the intuition that gas adsorption on a confined system (e.g., pores in a material) increases internal pressures and then leads to volumetric expansion", and describe the contraction as extraordinary. We would like to point out in this comment that adsorption-induced contraction of microporous materials is actually a very generic phenomenon, which has been demonstrated experimentally in a large range of microporous materials and explained theoretically. At the same time, we would like to acknowledge that the authors¹ should be credited for demonstrating this effect on the MOF-5 framework and characterizing its extent (of the order of 1% in volume). This is not atypical, if somewhat large, for inorganic microporous materials like zeolites, but small compared to metal-organic frameworks that show adsorption-induced structural transitions, such as the "breathing" MIL-53 ($\Delta V/V \sim 40\%$).

Nonmonotonic deformation in the course of guest adsorption is the norm, and not the exception, in microporous materials:² these materials contract at low pressure (low loading), and expand at higher gas pressure (higher loading). This behaviour has been observed experimentally and documented dating back to the 1940's³ in zeolites,^{4,5} microporous carbons,⁶⁻⁸ and metal–organic frameworks.⁹ A good review of experimental measurements can be found in ref. 2.

On the theoretical side, the contraction–expansion behaviour of microporous materials upon guest adsorption has also been well studied, both from the thermodynamic point of view based on the concept of adsorption stress^{9,10} and at the microscopic level using

^b Department of Chemical and Biochemical Engineering, Rutgers University, Piscataway, New Jersey 08854, USA





various molecular simulation tools.^{11–13} This phenomenon is ubiquitous, and does not depend on the specifics of host–guest interactions, adsorbate distribution within the pores, nor does it require low temperature to observe. At low gas pressure, *i.e.* at low loading, contraction of the material is driven by the host– guest dispersion attractive interactions (provided the pores of the material are large enough to accommodate the guest). As the gas pressure increases, *i.e.* at higher loading, the adsorbed phase becomes denser and the host–guest distances diminish to the point that short-range repulsive interactions come into play and cause the material to expand in order to accommodate additional guest molecules. This is schematized in Fig. 1.

References

- 1 J. Joo, H. Kim and S. S. Han, *Phys. Chem. Chem. Phys.*, 2013, **15**, 18822–18826.
- 2 A. V. Tvardovskiy, *Sorbent Deformation*, Elsevier, Amsterdam, The Netherlands, 2006.



^a Institut de Recherche de Chimie Paris, CNRS – Chimie ParisTech, 11 rue Pierre et Marie Curie, 75005 Paris, France.

E-mail: fx.coudert@chimie-paristech.fr

- 3 R. S. Haines and R. McIntosh, J. Chem. Phys., 1947, 15, 28-38.
- 4 B. P. Bering, O. K. Krasilnikova, A. I. Sarakhov, V. V. Serpinskii and M. M. Dubinin, *Bull. Acad. Sci. USSR Div. Chem. Sci.*, 1977, **26**, 2258–2261.
- 5 S. G. Sorenson, E. A. Payzant, W. T. Gibbons, B. Soydas, H. Kita, R. D. Noble and J. L. Falconer, *J. Membr. Sci.*, 2011, **366**, 413–420.
- 6 A. A. Fomkin, Adsorption, 2005, 11, 425-436.
- 7 J. R. Dacey and M. J. B. Evans, Carbon, 1971, 9, 579.
- 8 C. Balzer, G. Reichenauer and M. Wiener, in *Poromechanics V*, *Proceedings of the Fifth Biot Conference on Poromechanics*,

Vienna, ed. C. Hellmich, B. Pichler and D. Adam, 2013, pp. 701–709, DOI: 10.1061/9780784412992.083.

- 9 A. V. Neimark, F.-X. Coudert, A. Boutin and A. H. Fuchs, *J. Phys. Chem. Lett.*, 2010, **1**, 445–449.
- 10 P. I. Ravikovitch and A. V. Neimark, *Langmuir*, 2006, 22, 10864–10868.
- 11 P. Kowalczyk, A. Ciach and A. V. Neimark, *Langmuir*, 2008, 24, 6603–6608.
- 12 F. Ancilotto, M. W. Cole, A. Grosman, E. S. Hernández and F. Toigo, *J. Low Temp. Phys.*, 2011, **163**, 284–301.
- 13 D. Bousquet, F.-X. Coudert, A. V. Neimark, A. H. Fuchs and A. Boutin, *J. Chem. Phys.*, 2013, **138**, 174706.